

ID Material: R. Antich Revision: 6 Date: 1/25/19 **TF3025**

THERMOFIBER 3025 is a high kevlar laminate consisting of resin impregnated textile material non-metallic, with aramid components. This friction is stable across all working temperatures.

THERMOFIBER 3025 provides excellent wear life and consistent control and engagement characteristics. It is well suited for geared brake discs in industrial machinery.

Material Data

Friction Properties (according to graphics)

Static Friction Coefficient (15bar, from b	ox): 0.37±0.05	μ
Static Friction Coefficient (15bar, 100oC)	: 0.47±0.05	μ
Dynamic Friction Coefficient:	0.30±0.05	μ
Wear Rate:	25 (at 302 °F)	mm³/kwh
T [°] Fading:	>482	°F
Physical Properties		
Hardness (DIN53505):	90±5	Shore-D
Specific Gravity (ASTM D792): 1.4	15±0.05	gr/cm3
Ignition Loss (ASTM D7348):	30±2	%
Acetone Extraction (ASTM D494):	3±0.2	%
Thermal Conductivity (ASTM E1952): 0.	.3±0.01	W/m°K
Mechanical Properties		
Tensile Strength (ASTM D638):	47±5	N/mm ²
Compressive Strength (ISO 844:2014):	410±5	N/mm ²
Poisson Coefficient (ASTM D638):	0.255	
Young Modulus (ASTM D638): 133	54±100	N/mm ²
Recommended Working Values		
T° Max. Continuous Operation:	390	°F
T ^o Max Intermittent Operation:	190	° -

Material Type : Rigid material

Appearance / Formats




Applications

Forging machinery - Heavy duty static applications - Heavy-duty industrial machinery - Holding Mechanical Structures - Machinery Mining industries -

Price Level : \$ \$ \$ \$

Reach (EC) 1907/2006 - RoHS 2011/65/EU : Compliance		
Others		
Recommended Mating Surface:	Perlitic cast iron, hardness	
	HB150-200	
Recommended Adhesives:	Thermosetting adhesive	
Oil Resistant:	Yes	



Rubbing speed, temperature and pressure are related. Changing any values will change other. The values shown represent typical conditions, but are not ultimate limits of the material

www.protecfriction.com

answers@protecfriction.com